



Technical datasheet No.: **1505.7**
Product: VALMEX® FRONTLIT I easy
Article No.: 7536 5941.914/907

Type of coating and finish			
Type of coating	PVC		
Finish	one side lacquered (dull)		
Burning behaviour	ISO 3795 <100 mm/min.		
Total weight	415 g/m ²	EN ISO 2286-2	
Tensile strength warp/weft	2200 / 2100 N/50 mm	EN ISO 1421/V1	
Tear strength warp/weft	250 / 250 N	DIN 53363	
Adhesion	15 N/cm	PA 09.03 (intern)	
Cold resistance	-25 °C	EN 1876-1	
High Temperature	+70 °C	PA 07.04 (intern)	
Crack resistance	no cracks	100000 x	DIN 53359 A
Base fabric			
Material	PES	ISO 2076	
Yarn count	1100 dtex	ISO 2060	
Weave	L 1/1		

These indicated technical data are based on average results. Due to production procedures deviations up to -5% can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.