

The 3400 Series Nameplate UV Screen Ink has been formulated to meet the processing requirements of the membrane overlay market; including compatibility with most standard transfer adhesives, flexibility, opacity, ink to ink adhesion, and speed of cure. The 3400 Series is designed for second surface printing on polycarbonate and polyester used as membrane overlays where the lamination of pressure sensitive adhesive directly to the ink film may be necessary.

The 3400 Series may also be used for first surface printing on a variety of substrates; and for in mold decorating applications where a deep draw is not required.

The 3400 Series with the addition of 5% by weight NB80 UV Adhesion Promoter may also be printed over HP Indigo digital offset prints.

SUBSTRATES Polycarbonate, some top coated polyester (UV ink receptive primer).

USER INFORMATION

While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. See full disclaimer at the end of the document.

MESH 355 - 420 threads per inch (140 - 165 threads per cm) monofilament polyester mesh for most applications

STENCIL Solvent resistant, UV ink compatible direct emulsions and capillary films

SQUEEGEE 70 - 90 durometer shore hardness polyurethane squeegee

COVERAGE 2500 - 3800 square feet (232 - 353 square meters) per gallon depending upon ink deposit

PRINTING The 3400 Series ink is formulated to be press ready. Thoroughly mix the ink prior to printing. Maintain ink temperature at 65° - 90°F (18° - 32°C) for optimum print and cure performance. Lower temperatures increase the ink viscosity, impairing both flow and cure. Elevated temperatures lower the ink viscosity, reducing print definition, film thickness and opacity. Pretest to determine optimum printing performance for a particular set of ink, substrate, screen, press, and curing variables/conditions. The ink can be affected by stray UV light in and around a printing facility. Be aware of skylights, windows and overhead lights curing the ink in the screen. Light filters are recommended.

CURE PARAMETERS The 3400 Series ink cures when exposed to a medium pressure mercury vapor lamp set at 300 watts per inch with millijoules (mJ) and milliwatts (mW) of:

- > 300 mJ/cm² @ 800 mW/cm² for opaque whites and blacks
- > 200 mJ/cm² @ 800 mW/cm² for other colors

These guidelines are intended only as a starting point for determining cure parameters, which must be determined under actual production conditions.

To increase mJ levels, slow down the belt speed or scan speed. To increase mW levels, increase the wattage setting of the UV reactor. To optimize mJ and mW output, maintain the bulb and reflector condition and focus to the substrate.

The values mentioned above are representative of measurements taken using an EIT UVICURE Plus radiometer measuring the UVA bandwidth (320 - 390 nm). To obtain accurate readings with the UVICURE Plus, reduce the belt speed to less than 40 ft/min.

CLEARS / VARNISHES

Mixing Clear / Metallic Mixing Clear: Use 3426 Mixing Clear to reduce the density of colors or as a clear base for specialty additives such as Metallics.

ADDITIVES

All additives should be thoroughly mixed into the ink before each use. Prior to production, test any additive adjustment to the ink.

Reducer: Use RE 304 UV Reducer to reduce the viscosity of these inks. Add up to 10% by weight.

Adhesion Promoter: To gain additional adhesion performance to aged or difficult to adhere to substrates use NB80 UV Adhesion Promoter. Add up to 5% by weight. Improved adhesion will be demonstrated after 24 hours, with full cross linking in 3 to 7 days. Ink mixed with NB80 has a 4 to 8 hour pot life.

Anti-Blocking Additive: CARE101 3400 Anti-Blocking Additive may be added from 1% to 10% by weight to prevent the printed sheets from sticking while in a stack. The addition of CARE101 may reduce gloss; and the maximum level of addition must not be over 10% by weight.

CLEAN UP

Screen Wash (Prior to Reclaim): Use IMS203 Economy Graphic Screen Wash or IMS207C Graphic Re-circulating Wash.

Press Wash (On Press): Use IMS 301 Premium Graphic Press Wash.

STORAGE

Inks react to light and temperature. Store tightly covered at temperatures between 65° - 90°F (18° - 32°C). Ink taken from the press should not be returned to the original container; store separately to avoid contaminating unused ink.

PROCESSING

Die Cutting, Embossing, Forming: Allow the thoroughly cured ink film at least a 24 hour post cure.

Adhesive Lamination: It is recommended to wait 24 hours after printing before application of transfer adhesive. If a 24 hour wait is not possible due to production constraints, testing is recommended before actual production. Laboratory test results exhibited the possibility for laminating adhesives to be applied immediately. However, testing was conducted under controlled laboratory environment with thoroughly cured ink film. Since production environments vary, if adhesive needs to be applied immediately after printing and curing; the printer needs to pre-test before production.

In-Molding: The 3400 Series may be used in in-mold decorating applications where a deep draw is not required. A tie coat is necessary for printing over the cured ink film for maximum adhesion to the mold resin. The purpose of the tie coat is to create an adhesive layer between the cured ink film and the mold resin. Water-based tie coats are available from various suppliers. For recommendations on tie coats please call Nazdar Technical Services at 866-340-3579.

GENERAL INFORMATION

INK HANDLING

Direct skin contact to UV inks is the primary route of exposure and irritation. Therefore, it is recommended that all personnel handling these products wear gloves and barrier cream to prevent direct skin contact. Safety glasses are suggested in areas where ink may be splashed. If ink does come in contact with skin, wipe ink off with a clean, dry cloth (do not use solvent or reducer). Wash the affected area with soap and water. Consult the 3400 Series Material Safety Data Sheet for further instructions and warnings.

The 3400 Series is a one-part, 100% solids UV-curable screen printing ink and does not contain N-vinyl-2-pyrrolidone (trade name V-Pyrol®).

ADHESION TESTING

Even when recommended UV energy output levels are achieved, it is imperative to check adhesion on a **cooled down** print:

1. Touch of ink surface – the ink surface will be smooth and slick.
2. Thumb twist – the ink surface will not mar or smudge.
3. Scratch surface – the ink surface will resist scratching.
4. Cross hatch tape test – use a cross hatch tool or a sharp knife to cut through ink film only; then apply 3M #600 clear tape on cut area, rub down, wait for 1 minute and rip off at a 180 degree angle. Ink should only come off in actual cut areas.

Full adhesion characteristics are demonstrated within 24 hours after cure.

WEATHERING / OUTDOOR DURABILITY

The 3400 Series was formulated for second surface printing on membrane overlays for the appliance, automotive and other applications. The inks are not recommended for long-term outdoor exposure. If the inks are to be used in any type of outdoor application, whether printed first or second surface, the printer has the responsibility to test the inks and substrate to the end use specifications.

PRODUCT OFFERING

STANDARD PRINTING COLORS

The Standard Printing Colors have excellent opacity, flow characteristics, and are intended to work well from the container.

PANTONE MATCHING SYSTEM® BASE COLORS

The Pantone Matching System® Base Colors are used to simulate the Pantone® Color Formulation Guide. These inks are press ready, can be used in matches to achieve Pantone® color simulations, or let down with mixing clear. The ColorStar® Color Management System software provides blend formulations using Pantone Matching System® Base Colors. These blend formulations are also available at www.nazdar.com.

60 Series Colors: 3461 - 3469 colors have a high pigment concentration. These colors are formulated with some white or opaque pigment in order to increase opacity.

HALFTONE COLORS

Halftone Extender Base is used to reduce the density of any of the halftone colors.

Dense Halftone Colors are formulated with increased densities over the Standard Halftone densities, which are matched to the high end of the SWOP standards, and are designed for printers that want to have the latitude to adjust the density levels of their halftone inks.

SINGLE PIGMENT TONERS

The Single Pigment Toners produce clean and vibrant colors and are press ready. The Single Pigment Toners can be used in color matches, or let down with mixing clear.

TEXTURED CLEARS

Various clears for selective texturing are available as well as a UV-curable lens clear for windows. The clears are for top or first surface application only.

SPECIAL ADDITIVES

When inks are to be printed over a special effect color, the overprinting ink(s) must be evaluated for inter-coat adhesion before proceeding with the production run. To maximize inter-coat adhesion, specialty colors should be printed as late as possible in the print sequence.

The following special effect pigments may be added to 3400 Series. These pigments are available in 1-pound containers. Contact Nazdar for the item number(s) and availability of special effect products. Pigments may settle in the container; prior to printing, thoroughly mix the ink.

Silver (aluminum) Metallic: add up to 8% by weight.

Gold (bronze) Metallic: add up to 15% by weight.

Mix only enough metallic ink to be used the same day. Chemical reactions in metallic inks may result in viscosity, color and printability changes over time.

Pearlescents / Interference Pigments: add up to 20% by weight.

Multi-Chromatic Pigments: add up to 10% by weight.

See the Pearlescent, Interference, and Multi-Chromatic Technical Data Sheets for more information.

Pantone® 871c to 877c has been matched in 3400 Series Ink using Pearlescent Pigments.

Phosphorescents: add up to 20% by weight.

Fluorescents: add up to 25% by weight. Fluorescent colors fade quickly with exposure to ultraviolet light. This includes outdoor exposure as well as UV reactor exposure.

COLOR CARD MATERIALS

The following is a list of screen printed samples available.

3400 Series UV Screen Ink Color Card: shows all standard 3400 colors.

UV Texture Clears Color Card: shows all standard UV texture clears available, including air texture clears and nitrogen texture clears.

NSC UV Crystal Clear Transparent Ink Color Card: shows standard high density crystal clear transparent colors designed to print on windows.

60/360 Color Card: shows comparisons between the 60 Series and the 360 Series Pantone Matching System® Base Colors.

Special Effects Color Card: shows Metallic, Pearlescent, Interference, and Multi-Chromatic effects mixed with clear.

Non-Metallic Pantone® Simulations Sheet: shows representations of the 871c to 877c Pantone® Metallic color matches using pearlescent pigments.

PACKAGING All items listed below are available in quart and gallon containers.

Stock Number	Standard Printing Colors	Stock Number	Pantone Matching System® Base Colors
3411*	Lemon Yellow	3426	Mixing Clear
3419*	Fire Red	3458	Tinting White
3420*	Orange	3459	Tinting Black
3477	Super Opaque Black	3461	Yellow
3478	High Intensity White	3462*	Warm Red
3479	High Intensity Black	3463	Rubine Red
3496	Jet Black	3464	Rhodamine Red
3498	Bright White	3465	Purple
3499	Black Concentrate	3466	Violet
		3467	Reflex Blue
		3468	Process Blue
		3469	Green
Stock Number	Single Pigment Toners	Stock Number	Halftone Colors
3480	Yellow Toner (GS)	3490	Halftone Extender Base
3481	Orange Toner	34101	Halftone Cyan Dense
3482	Carmine Toner	34102	Halftone Magenta Dense
3483	Magenta Toner	34103	Halftone Yellow Dense
3484	Maroon Toner	34104	Halftone Black Dense
3485	Green Toner		
3486	Blue Toner (GS)		
3487	Blue Toner (RS)		
3488	Violet Toner		
3489	Red Toner		
34PB12	Medium Yellow (RS)		
34PB18	Red (BS)		
34PB24	Deadfront Black		
34PB60	Red (YS)		
Stock Number	Clears for Selective Texturing**	Stock Number	Clears for Selective Texturing**
NSC40	UV Air Texture Clear Fine	PSPC27	Very Coarse Nitrogen TC
NSC41	UV Air Texture Clear	PSPC27G	Coarse Nitrogen TC
NSC42C	Nitrogen TC Coarse (4-gallon minimum)	PSPC27H	Very Fine Nitrogen TC
NSC42F	Nitrogen TC Fine (4-gallon minimum)	PSPC27T	Fine Nitrogen TC
NSC43	Lens Clear	PSPC27TS	Satin Nitrogen TC
		PSPC27Y	Fine Nitrogen TC

Stock Number	Clears for Selective Texturing**
NSC47	UV Air Texture Very Fine
NSC48	UV Air Texture Medium
NSC49	UV Air Texture Coarse
NSC50	UV Air Texture Very Coarse

*These colors are not recommended in applications that require high heat during processing.

** Refer to the Technical Data Sheet for each clear for detailed information on these inks. These clears are for first or top surface printing only.

PACKAGING

Additives/Reducers are available in quart and gallon containers.
Cleaners are available in gallon, 5 gallon and 55 gallon containers.

Stock Number	Additives/Reducers	Stock Number	Cleaners
RE304	UV Reducer	IMS203	Economy Graphic Screen Wash
NB80	UV Adhesion Promoter (quarts only)	IMS207C	Graphic Re-circulating Wash
CARE101	3400 Anti-Blocking Additive	IMS301	Premium Graphic Press Wash

Nazdar® stands behind the quality of this product. Nazdar® cannot, however, guarantee the finished results because Nazdar® exercises no control over individual operating conditions and production procedures. While technical information and advice on the use of this product is provided in good faith, the User bears sole responsibility for selecting the appropriate product for their end-use requirements. Users are also responsible for testing to determine that our product will perform as expected during the printed item's entire life-cycle from printing, post-print processing, and shipment to end-use. This product has been specially formulated for screen printing, and it has not been tested for application by any other method. Any liability associated with the use of this product is limited to the value of the product purchased from Nazdar®.

Based on information from our raw material suppliers, these products are formulated to contain less than 0.06% lead. If exact heavy metal content is required, independent lab analysis is recommended.

Nazdar Worldwide Headquarters
8501 Hedge Lane Terrace, Shawnee, KS 66227-3290 USA
Toll Free: 866.340.3579 or Tel: 913.422.1888 Fax: 913.422.2296
e-mail: custserv@nazdar.com

Nazdar Limited
Barton Road, Heaton Mersey, Stockport, England SK4 3EG
Tel: + (44) 0.161.442.2111 Fax: + (44) 0.161.442.2001
e-mail: technicalservicesuk@nazdar.com

<http://www.nazdar.com>